

Laboratory Data

Particulars	English	Metric
Flashpoint; PMCC	100°C	38°C
Specific Gravity @ 60°F (15.6°C)	0.87	0.87
Recommended Dry Film Thickness	1.0 mils	25 microns
Theoretical Coverage @ Avg. Recommended DFT	916 sq. ft./ U.S gallon	22.5 sq. meters/ liter
Approximate Air Dry Time @ 77(25)	1 hour	-
Volatile Organic Content (VOC)	2.93 lbs/ US gallon	351 grams/ liter
Accelerated Corrosion Tests		
5% Salt Spray (Hours)	-	-
*ASTM B-117 @ 1.0 mils, (2×4×1/8 in. Polished Steel Panels)	<u>2000</u>	=
**DIN 50021 @ 25 microns, (125×200mm. DIN 1623 Panels) Applicable U.S. Military Specifications Mil-c-16173-d; Grade 2	=	<u>2000</u>
	-	-