

## Laboratory Data

Particulars	English	Metric
Flashpoint; PMCC	105°F	40°C
Specific Gravity @ 60°F (15.6°C)	0.90	
Recommended Dry Film Thickness	2.5 mils	62.5 microns
Theoretical Coverage @ Avg. Recommended DFT	347 sq. ft./ U.S gallon	8.5 sq. meters/ liter
Approximate Air Dry Time @ 77°F (25)	1-2hour	-
Volatile Organic Content (VOC)	3.15 lbs/ US gallon	377 grams/ liter
<b>Accelerated Corrosion Tests</b>		
5% Salt Spray (Hours)	-	-
*ASTM B-117 @ Recommended DFT	<u>1500</u>	=
(2×4×1/8 in. Polished Steel Panels)	-	-
**DIN 50021 @ Recommended DFT,	=	<u>300</u>
(125×200mm. DIN 1623 Panels) **ASTM (American Society for Testing and Materials) * DIN (Deutsche Industry Norman)	-	-