

Laboratory Data

Particulars	English	Metric
Flashpoint; PMCC	100°C	38°C
Specific Gravity @ 60°F (15.6°C)	0.88	0.88
Recommended Dry Film Thickness	1.3 mils	32.5 microns
Theoretical Coverage @ Avg. Recommended DFT	630 sq. ft./ U.S gallon	15.4 sq. meters/ liter
Approximate Air Dry Time @ 77°C (25°C)	1hour	1hour
Volatile Organic Content (VOC)	3.24 lbs/ US gallon	400 grams/ liter
Accelerated Corrosion Tests		
5% Salt Spray (Hours)	-	-
*ASTM B-117 @ 1.3 mils, (2×4×1/8 in. Polished Steel Panels)	<u>2000</u>	=
**DIN 50021 @ 32.5 microns, (125×200mm. DIN 1623 Panels)	=	<u>168</u>
**ASTM (American Society for Testing and Materials) * DIN (Deutsche Industry Norman)	-	-