

Technical Specification

Chemical and Physical Properties	Test Method	Typical Data
Flash point (COC)	ASTM D 92	110 °C
Density at 15 °C	ASTM D 1298	0.880 g/ml
Viscosity at 40°C	ASTM D 445	12 cSt
Pour point		-12 °C
Volatiles (% weight)		5
Film thickness		5 microns
Application method		Spray, dip, brush

Specification

Corrosion Protection Properties	Test Method	Typical Data
Vapour phase protection	MIL-P-46002A	Passes
Humidity chamber test (100% RH at 48°C)	JAN-H-792	100 hours